



**Sterling Supplies - Black Anti-Slip Tape 50mm - Wet Sliptest MO140722-11A**

14 Jul 2022

**Slip Resistance Classification of New Pedestrian Surfaces - AS4586:2013 Appendix A**

Date Tested:	14 Jul 2022
Test Report Number:	MO140722-11A
Client Name & Address:	Sterling Supplies - 28-34 Paraweena Drive Truganina Victoria 3029
Test Site / Surface Tested :	Black Anti-Slip Tape 50mm - Rough
Sample Information :	Samples and Test Information Supplied by Client
Wet Pendulum Test carried out using :	Slider 55 (TRL) Rubber slider
Temp Correction for Type 55 (TRL) Slider	15-17 = -1
Any Variations to Standards	Variation of Standards - 3 Strips available for Testing
Testing Officer / Approved Signatory:	Mitchell Ording
Pendulum in use - Calibration Date :	#SK2072 - Wessex Portable Skid Tester (C : 07.05.21)
Signature of Approved Signatory :	

**Test Results :**

Sample No.	Swing 1	Swing 2	Swing 3	Swing 4	Swing 5	Mean BPN of last 3 swings :	SCV :	Surface Picture
Area 1	95	95	95	95	95	95	N/A	
Area 2	96	96	95	95	95	95	N/A	
Area 3	95	95	94	94	94	94	N/A	

Variation to Standard Mean BPN Slip Resistance Value (SRV) 94

Corrected Mean BPN (SRV) Slider 55 ONLY 93

CLASSIFICATION using Slider 55 (TRL Slider) P5 = >44

Accredited for Compliance with ISO/IEC 17025. The information presented herein and on the Sliptest Report is copyright and is protected by copyright law, any reproduction of this information and test report except in full is prohibited. Sliptest Australia Pty. Ltd. performed this on site test with reference to the following Australian Standard testing criteria, of AS 4586:2013 Classification of new pedestrian surface materials. Appendix A - Wet Pendulum Test Method and Hand Book HB 198: 2014 with reference to AS/NZS 4663: 2004 Slip Resistance measurement of existing pedestrian surfaces and HB 197: 1999. These results do not account for Future Wear, Maintenance or Contamination of this surface once in-situ.

