

Slip Check to AS 4586-2013

Appular - Ribbed

Report Number: M0386c

Report Date: 13 November 2017

Total Number of Pages 2

NATA Accreditation Number 17139

Accredited for compliance with ISO/IEC 17025 – Testing

The results of the tests, calibrations and/or measurements included in this document are traceable to Australian/national standards

NATA is a signatory to the ILAC Mutual Recognition Arrangement for the mutual recognition of the equivalence of testing, medical testing, calibration and inspection reports

Issued by

Safe Environments Pty Ltd
Unit 4, 40 Bessemer Street
Blacktown NSW 2148

Prepared for

Sterling Supplies
PO Box 9262
Scoresby VIC 3179

Approved by


Ryan Voorderhake
Authorised Signatory

13 November 2017

Test Report No. M0386c

Slip Resistance Classification of New Pedestrian Surface Materials

AS 4586-2013 Appendix A (Wet Pendulum Test)

The slip resistance classification has been determined for unused surfaces using specific conditions. Factors such as usage, cleaning systems, applied coatings and patterns of wear may affect the characteristics of the surface after classification. Standards Australia Handbook 198:2014 *Guide to the specification and testing of slip resistance of pedestrian surfaces* provides guidance for the selection of slip resistant pedestrian surfaces classified in accordance with AS 4586-2013. It is recommended that this test report be read in conjunction with AS 4586 and HB 198.

Requested by: Sterling Supplies
Client Address: PO Box 9262
Scoresby VIC 3179
Product Manufacturer: Sterling Supplies
Product Description: Appular - Ribbed

Test conducted according to: AS 4586:2013 Appendix A
Location: Level 1, 420 Spencer Street, West Melbourne VIC 3003
Conducted by: Nasser Cura

Date:	13 November 2017	Temperature:	25°C
Sample:	Unfixed	Cleaning:	None
Rubber slider used:	Slider 96	Conditioned:	Grade P 400 paper dry followed by wet lapping film
Slope of specimen:	Tested on a flat level surface		
Direction of Test:	Perpendicular to profile		

	Specimen 1	Specimen 2	Specimen 3	Specimen 4	Specimen 5
Mean BPN of last 3 swings:	59	60	59	58	57

Reported SRV of Sample:	59
Class:	P5