

## **Slip Check to AS 4586-2013 Duratac 3030 Direction Tactile**

**Report Number: M0361**

**Report Date: 7 September 2017**

**Total Number of Pages 2**

NATA Accreditation Number 17139

Accredited for compliance with ISO/IEC 17025 – Testing

The results of the tests, calibrations and/or measurements included in this document are traceable to Australian/national standards

NATA is a signatory to the ILAC Mutual Recognition Arrangement for the mutual recognition of the equivalence of testing, medical testing, calibration and inspection reports

**Issued by**

Safe Environments Pty Ltd  
Unit 4, 40 Bessemer Street  
Blacktown NSW 2148

**Prepared for**

Sterling Supplies  
PO Box 9262  
Scoresby VIC 3179

**Approved by**

  
Ryan Voorderhake  
Authorised Signatory

7 September 2017

## Test Report No. M0361

### Slip Resistance Classification of New Pedestrian Surface Materials

AS 4586-2013 Appendix A (Wet Pendulum Test)

The slip resistance classification has been determined for unused surfaces using specific conditions. Factors such as usage, cleaning systems, applied coatings and patterns of wear may affect the characteristics of the surface after classification. Standards Australia Handbook 198:2014 *Guide to the specification and testing of slip resistance of pedestrian surfaces* provides guidance for the selection of slip resistant pedestrian surfaces classified in accordance with AS 4586-2013. It is recommended that this test report be read in conjunction with AS 4586 and HB 198.

Requested by: Sterling Supplies  
Client Address: PO Box 9262  
Scoresby VIC 3179  
Product Manufacturer: Sterling Supplies  
Product Description: Duratac 3030 Direction Tactile

Test conducted according to: AS 4586:2013 Appendix A  
Location: Level 7, 552 Lonsdale Street, Melbourne VIC 3000  
Conducted by: Nasser Cura

Date:	07 September 2017	Temperature:	21°C
Sample:	Unfixed	Cleaning:	None
Rubber slider used:	Slider 96	Conditioned:	Grade P 400 paper dry followed by wet lapping film
Slope of specimen:	Tested on a flat level surface		
Direction of Test:	Approximately 10° to profile		

	Specimen 1	Specimen 2	Specimen 3	Specimen 4	Specimen 5
Mean BPN of last 3 swings:	30	30	27	29	27

<b>Reported SRV of Sample:</b>	<b>29</b>
<b>Class:</b>	<b>P2</b>